

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 184 353 A1

(12)

EUROPEAN PATENT APPLICATION
published in accordance with Art. 158(3) EPC

(43) Date of publication:
06.03.2002 Bulletin 2002/10

(51) Int Cl.7: **C04B 24/26**, C04B 103/40,
C08F 290/06, C08F 299/02,
B01F 17/00

(21) Application number: 99961354.0

(22) Date of filing: 24.12.1999

(86) International application number:
PCT/JP99/07261

(87) International publication number:
WO 00/39045 (06.07.2000 Gazette 2000/27)

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE

(30) Priority: 25.12.1998 JP 37686298

(71) Applicant: Sika Ltd.
Hiratsuka-shi, Kanagawa 254-0021 (JP)

(72) Inventors:
• AMAYA, Toshihiko
Yokohama-shi, Kanagawa 241-0816 (JP)
• IKEDA, Akira
Funabashi-shi, Chiba 273-0026 (JP)
• IMAMURA, Jun
Hiratsuka-shi, Kanagawa 254-0072 (JP)

• KOBAYASHI, Atsushi
Hiratsuka-shi, Kanagawa 254-0017 (JP)
• SAITO, Kaname
Yokohama-shi, Kanagawa 244-0816 (JP)
• DANZINGER, Wernher, M.
Hiratsuka-shi, Kanagawa 254-0034 (JP)
• TOMOYOSE, Tetsu
Chigasaki-shi, Kanagawa 253-0086 (JP)

(74) Representative:
Patentanwälte Schaad, Balass, Menzi & Partner
AG
Dufourstrasse 101 Postfach
8034 Zürich (CH)

(54) CEMENT DISPERSANT AND CONCRETE COMPOSITION CONTAINING THE DISPERSANT

(57) A cement dispersant (especially a dispersant for concretes with ultrahigh performance) comprising as a main component a water-soluble amphoteric copolymer obtained by copolymerizing (A) a polyamide-polyamine of an alkylene oxide adduct thereof with (B) (meth)acrylic acid or an alkali metal, ammonium, or alkanolamine salt thereof and (C) a polyalkylene glycol

ester of (meth)acrylic acid in an A/B/C ratio of (10-40)/(10-40)/(50-80)(wt.%); and a concrete composition (especially an ultra high-performance concrete) containing the dispersant. The dispersant satisfies all of a water-reducing effect, slump flow retention, strength development, etc.

EP 1 184 353 A1

DescriptionTechnical Field

[0001] The present invention relates to a cement dispersant and a concrete composition containing the dispersant. In more detail, the present invention relates to a cement dispersant having superior dispersion effect of cement particles and its retention, thereby obtaining greater water-reducing effect and long slump flow retention, so that a workability is excellent and strength development after hardening is good, particularly a cement dispersant suitable for concretes with ultrahigh performance, and a concrete composition such as an ultrahigh performance concrete composition containing the dispersant.

Background Art

[0002] Polycarboxylic acid type dispersants such as a copolymer of polymelamine sulfonate, lignin sulfonate, olefin and maleic acid and the like have conventionally been used as a cement dispersant. However, these compounds have problems in not only their effect connoting as slump flow retention effect, but their suitability in existing as well as future ultrahigh performance concrete.

[0003] New type polycarboxylic acid type cement dispersants having nonionic groups introduced therein are positively proposed to solve these problems. For example, JP-A 1-226757 discloses a copolymer of (meth)acrylate, (meth) acryl sulfonate, and monoacrylate ester of polyethylene glycol alkyl ether or monoacrylate ester of polypropylene glycol alkyl ether. However, conventional cement dispersants including the one disclosed in the above publication have not yet been satisfactory as to all of water reducing effect, slump flow retention, strength development and the like in order to use as a compounded concrete with said dispersants.

[0004] Therefore, there is a strong call in the industry for cement dispersants meeting sufficient water reducing effect, slump flow retention, strength development and the like, applicable even to ultrahigh performance concrete.

[0005] The present invention has been made to meet this demand, and has an object to provide a cement dispersant with satisfactory water reducing effect, slump flow retention, strength development and the like, and a concrete composition containing said dispersant in order to solve the problems existing in the prior art.


Disclosure of Invention

[0006] After extensive investigation into finding the solution for the problems, the present inventors have found a copolymer comprising three specific organic substances with the desired effect, and have completed the present invention as described.

[0007] That is, the present invention relates to a cement dispersant comprising a water soluble amphoteric copolymer, as a main component, obtained by copolymerizing an addition product (compound A) obtained by the addition of 0-8 moles of an alkylene oxide having 2 to 4 carbon atoms to one equivalent of amino residues in polyamide polyamine obtained by condensation of 1.0 mole of a polyalkylene polyamine, 0.8-0.95 mole of a dibasic acid or an ester of the dibasic acid with a lower alcohol having 1 to 4 carbon atoms, and 0.05-0.18 mole of acrylic acid or methacrylic acid, or an ester of acrylic acid or methacrylic acid with a lower alcohol having 1 to 4 carbon atoms, and a compound (compound B) of the formula I:



(wherein R is hydrogen atom or methyl group, and M is hydrogen atom, alkali metal, ammonium group or alkanolammonium group), and a compound (compound C) of the formula II:



(wherein R' is hydrogen atom or methyl group, R₁ is C₂-C₄ alkylene group, R₂ is hydrogen atom or C₁-C₄ alkyl group, and m is an integer of 1 to 100), in the ratio of compound A : compound B : compound C = 10-40% by weight : 10-40% by weight : 50-80% by weight.

[0008] The present invention also particularly relates to said cement dispersant of the present invention used in an ultrahigh performance concrete composition.

[0009] The cement dispersant of the present invention can also be used as a general purpose high performance AE water reducing agent by blending techniques available for regular concrete.

[0010] The present invention further relates to a concrete composition characterized by having said cement dispersant of the present invention, and particularly the concrete composition for an ultrahigh-performance concrete. The "ultrahigh performance concrete" described herewith denotes concrete generally used and understood in the pertinent art, and encompasses concretes in considerably broad range, and includes, for example, concrete showing strength equal to or higher than the conventional concrete even when less amount of water is used as compared with the conventional concrete, or more specifically concrete that provides a highly workable ready-mixed concrete without interfering in general use even when a water/binder ratio is 20% or less, particularly about 12%, and yet with a compression strength of 150 N/mm² or more upon hardening.

[0011] As described above, the compound A used in the present invention is an addition product obtained by the addition of specific amount of an alkylene oxide (compound d) to the polyamide polyamine achieved by condensation of a polyalkylene polyamine (compound a), a dibasic acid or an ester of the dibasic acid with a lower alcohol having 1 to 4 carbon atoms (compound b), and acrylic acid or methacrylic acid, or an ester of acrylic acid or methacrylic acid with a lower alcohol having 1 to 4 carbon atoms (compound c), in a definite proportion.

[0012] Examples of the polyalkylene polyamine of the compound a include diethylene triamine, triethylene tetramine, tetraethylene pentamine, pentaethylene hexamine, dipropylene triamine, tripropylene tetramine and tetrapropylene pentamine, but diethylene triamine and triethylene tetramine are preferable from both points of effectiveness and economical angle.

[0013] Examples of the dibasic acid and its lower alcohol ester having 1 to 4 carbon atoms of the compound b include, for example, malonic acid, succinic acid, fumaric acid, maleic acid, glutaric acid, adipic acid, pimelic acid, phthalic acid, azelaic acid, sebacic acid, and their esters with lower alcohols having 1 to 4 carbon atoms such as methanol, ethanol, propanol or butanol, or their isomers, if present. Of those, adipic acid is most preferable from both effectiveness and economical angle.

[0014] Examples of acrylic acid or methacrylic acid and its lower alcohol ester having 1 to 4 carbon atoms, of the compound c include, for example, acrylic acid, methacrylic acid, methyl acrylate, methyl methacrylate, ethyl acrylate, ethyl methacrylate, propyl acrylate, propyl methacrylate, butyl acrylate and butyl methacrylate.

[0015] The polyamide polyamine comprising three components of the above compounds a, b and c can easily be obtained by the conventional polycondensation technique.

[0016] The alkylene oxide having 2 to 4 carbon atoms, which is the compound d, to be added to amino residue of polyamide polyamine is ethylene oxide, propylene oxide or butylene oxide. One or more of alkylene oxides described may be used.

[0017] Preparation of the polyamide polyamine, inter alia, polycondensation reaction of the compounds a, b and c, may be two-step reaction comprising polycondensation of only the compound a and the compound b, thereafter further polycondensation with the compound c as a monobasic acid, or one step reaction comprising simultaneous polycondensation with the compounds a, b and c from the start.

[0018] However, either method leads to the same polycondensation reaction, that is amidation reaction in which acrylic acid residue or methacrylic acid residue of the compound c are ultimately found at the end of a polyamide chain since the amidation reaction proceeds in parallel to amide interchange reaction.

[0019] Following is a reaction molar ratio of the three components constituting the polyamide polyamine described below.

[0020] The reaction molar ratio of the compound b (dibasic acid or its ester) to one mole of the compound a (polyalkylene polyamine) is 0.8-0.95 mole. Polycondensation product of the compound a and the compound b in molar ratio defined above produces, on the average, a polyamide with a certain chain length, comprising polycondensation of from (polyalkylene polyamine 5 moles : dibasic acid 4 moles) to (polyalkylene polyamine 20 moles : dibasic acid 19 moles),

and therefore, the dispersant obtained by using the polyamide exhibits high water reducing property and slump flow retention. When the chain length of this polyamide is shorter than the case described above (the reaction ratio is less than 0.8 mole), the dispersant obtained by using the polyamide shorter in chain length has markedly decreased slump flow retention. If the chain length is longer than the above (the reaction ratio exceeding 0.95 mole), water reducing property considerably decreases, which is not desirable.

[0021] The polyamide polyamine according to the present invention has acrylic acid residue or methacrylic acid residue of 0.25 mole (in the case of a:b:c=1.0:0.8:0.05 (mole)) to 3.6 moles (in the case of a:b:c=1.0:0.95:0.18 (mole)), but the preferable range is 0.5-2.0 moles from the standpoint of effect. When the value is lower than 0.25 mole (for example, in the case of a:b=1.0:0.8 and that quantity ratio of compound c to compound a is less than 0.05), the proportion of the compound A obtained from this ratio in the final copolymer decreases, and property as a cement dispersant is substantially diminished. On the other hand, if it exceeds 3.6 moles (for example, in the case of a:b=1.0:0.95 and that quantity ratio of the compound c to the compound a exceeds 0.18), over formation of the three-dimensional structure of the copolymer is observed and a sufficient effect can not be obtained.

[0022] Amount of alkylene oxide to be added to the polyamide polyamine is 0-8 moles per one equivalent of amino residue of the polyamide polyamine. If it exceeds 8 moles, molecular weight of the compound A increases with inevitable decrease in cation equivalent and sufficient effect as the amphoteric polymer expected of the present invention is not obtained. The addition of the alkylene oxide in the present invention is desirable and the amount thereof is preferably 0.5-6.0, most preferably 1.0-5.5, to one equivalent of amino residue of the polyamide polyamine.

[0023] Examples of the compound B used in the present invention include acrylic acid or methacrylic acid, and their sodium, potassium, ammonium, monoethanol amine, diethanol amine or triethanol amine salts, but sodium or ammonium salts are preferable from the standpoints of effectiveness and economical efficiency.

[0024] Examples of the compound C used in the present invention include methacrylic acid esters or acrylic acid esters of methoxypolyethylene glycol, methacrylic acid esters or acrylic acid esters of ethoxypolyethylene glycol, methacrylic acid esters or acrylic acid esters of methoxypolyethylene glycol/polypropylene glycol copolymer, and monoacrylic acid or monomethacrylic acid esters of polyethylene glycol.

[0025] Production of the water-soluble amphoteric copolymer in the present invention can easily be carried out using the compound A, the compound B and the compound C by the conventional method in the pertinent art.

[0026] Copolymerization ratio of compound A:compound B:compound C in the copolymer of the present invention is in a range of 10-40:10-40:50-80, and is appropriately selected such that the sum is 100 as the weight basis. If the ratio is outside the above range, the effects below can not be obtained.

[0027] The water soluble amphoteric copolymer thus obtained in the present invention has the characteristic of having extremely superior water reducing property and prolonged slump flow retention as a cement dispersant, and is possible to exhibit the performance that has not been achieved as cement dispersants heretofore in use or otherwise proposed. These advantages seemed to be brought about by having a nonionic hydrophilic group comprising carboxyl group (anionic group), polyalkylene polyamide group (cationic group) and alkoxypolyalkylene glycol group in the molecular structure of the copolymer, and thus the basic concept of the present invention is in the use of the copolymer having such a unique structure. In particular, the copolymer having specific amide group functioning as cationic radical has not yet heretofore been proposed, and therefore striking effect that has been observed but not predicted is in fact surprising. JP-A 7-33496 discloses the technique in which polyamide polyamine is incorporated as a copolymer component for cement dispersant, however, a copolymer using the polyamide polyamine defined in the technique disclosed by JP-A 7-33496 has the limit in water-reducing property, slump flow retention, hardening and the like when water/cement ratio or water/binder ratio in a concrete is 30% or less, and thus superior water reducing property and slump flow retention observed in the present invention can not be expected.

[0028] In general, it is known that use of a polymer type compound having many anionic groups in the molecule is effective as a dispersant in order to disperse substances with positively charged surface such as cement particles as well as to retain its fluidity in the presence of a small amount of water.

[0029] It is known that anion moiety of polymer adsorbs positively charged particles and neutralize them, and the polymer thus adsorbed provides good dispersion system by its electric repulsion force of negative charges, and it is also generally discussed that fluidity of dispersion system is likely to be enhanced with stronger electric repulsion force among particles.

[0030] It is apparent that sulfonic acid group which is an anionic group functions in, for example, β -naphthalenesulfonic acid/formalin high condensate or the like, and carboxyl group which is an anionic group functions in salt of lower α -olefin/maleic anhydride copolymer or sodium polyacrylate.

[0031] Further, it is said that (meth)acrylic acid/alkoxypolyethoxy(meth)acrylate copolymer and the like can exhibit their dispersion and fluidity by that carboxyl group and bulky alkoxypolyalkylene glycol group acting among particles.

[0032] However, it is the state of art for these currently available compounds that there is the limit in fluidity effect for an ultrahigh-performance concrete with a small amount of water present, and the problem on slump flow retention can not be solved. Further, it is possible to add an excess amount of water in order to achieve an initial fluidity, but this

is out of the question as a concrete for structures as setting becomes extremely slow with acute possibility of poor hardening.

[0033] As a result of investigations into various copolymers, the present inventors have finally found the copolymer described in the present invention far superior to the performance of currently available compounds and are trying to elucidate such a mechanism at the present time.

[0034] It is considered that the polycarboxyl groups of the water-soluble amphoteric copolymer according to the present invention participates in neutralization of charges as well as an electric repulsion force among cement particles, and it is supposed that the terminal hydroxyl group of the polyamide polyamine group greatly influences in slump flow retention with the cationic group moiety having the specific amide group in the present invention showing some charge regulating action.

[0035] Further, it is supposed that carboxyl group, alkoxypolyalkylene glycol group and polyamide polyamine group which constitute the compound of the present invention sufficiently bear their corresponding roles in achieving good effect in the dispersion system, and yet the synergistic action among them have been demonstrating remarkable effect.

Best Mode for Carrying Out the Invention

[0036] Although the amount of the cement dispersant comprising the water-soluble amphoteric copolymer of the present invention to be added varies depending on the compounding conditions including materials used in said concrete, as a general rule, about 0.1-1.5% in terms of the solid content in cement is added. That is, the more dispersant added, the better water reducing property and slump flow retention are. However, setting retardation and in the worst case, poor hardening may be observed if the amount added is too much excess. The way to use the present invention is the same as in currently available general cement dispersants, and the cement dispersant of the present invention is added in the form of a stock solution at the time of kneading concrete or in previously diluted form with kneading water. Alternatively, the dispersant may be added after kneading a concrete or a mortar, and the resulting mixture may again be kneaded to comparable homogeneity.

[0037] The present invention also relates to a concrete composition containing said cement dispersant of the present invention. Components other than the cement dispersant described are the conventionally used components for concrete such as ordinary Portland cement, early-strength Portland cement, low heat-moderate heat Portland cements or blast furnace cement for cements, fine aggregates or coarse aggregates for aggregates, silica fume, calcium carbonate powder or slag powder for admixtures, expanding agent, and water. It is needless to say that the conventional dispersants, water reducing agents, air entraining agents, defoaming agents and the like, other than the dispersant of the present invention, can appropriately be compounded. The compounding proportion of each of these components can easily be determined according to the kind of component selected and objectives.

Examples

[0038] The present invention is described further in more details by showing the examples, but the invention is not limited to the particular embodiments described herein.

I. Synthesis of water-soluble amphoteric copolymer

Example 1

[0039] Diethylene triamine 103 g (1.0 mole) and adipic acid 125 g (0.86 mole) were charged in a reaction vessel equipped with a stirrer, and mixed by stirring under a nitrogen atmosphere by introduction of nitrogen. Temperature was adjusted to 150°C, and the reaction was continued for 20 hours until acid value reaches 18 while removing water of reaction product accompanied with polycondensation. Next, hydroquinone methyl ether 0.3 g and methacrylic acid 12.3 g (0.14 mole) were charged, and reacted at the same temperature (150°C) for 10 hours. By this, polyamide polyamine 209 g (melting point 110°C, acid value 19) was obtained together with 32 g in total of reaction distilled water. The total amount of the polyamide polyamine thus obtained was dissolved in water 503 g, and temperature was adjusted to 50°C. Ethylene oxide 127 g (corresponding to 2.0 moles to the total amino residue including unreacted amino group) was sequentially added over 2 hours at the same temperature (50°C), and matured for 2 hours. Compound A-1 (solid content 40%) 839 g of the present invention was obtained.

[0040] Water 1,270 g was charged in a reaction vessel equipped with a stirrer, and nitrogen was introduced to make the inside of synthesis system to be a nitrogen atmosphere and temperature was adjusted to 90°C. Three solutions of a mixture of compound A-1 500 g, sodium methacrylate salt (compound B) 200 g and methoxypolyethylene glycol monomethacrylate (compound C, molecular weight 2,000) 600 g (compound A/compound B/compound C=20 parts by weight/20 parts by weight/60 parts by weight in terms of weight ratio of solid content, the total being 100 parts by

EP 1 184 353 A1

weight), 5% ammonium thioglycolate aqueous solution 400 g and 5% ammonium persulfate aqueous solution 400 g were simultaneously added dropwise to the synthesis system over 2 hours. After completion of the dropwise addition, 5% ammonium persulfate aqueous solution 100 g was further added dropwise over 30 minutes, and maturation was then conducted for 2 hours to obtain 3,470 g of a water soluble amphoteric copolymer (Example 1).

[0041] This copolymer (Example 1) was a copolymer having a weight average molecular weight by GPC molecular weight measurement of 32,000. The measurement conditions are as follows.

Column: OHPak SB-802HQ, OHPak SB-803HQ, OHPak SB-804HQ (products of Showa Denko K.K.)

Eluate: Ratio of 50 mM sodium nitrate aqueous solution and acetonitrile 80:20

Detector: Differential refractometer

M.W. Calibration standard: Polyethylene glycol

Examples 2-9

[0042] Using starting materials as in Table 1, polyamide polyamine alkylene oxide adduct compounds A-2 to A-7 were obtained in the same manner as in Example 1.

[0043] Using compound A, compound B and compound C as in Table 2, copolymerization was conducted in the same manner as in Example 1 to obtain water soluble amphoteric copolymers (Examples 2-9) (water content of the copolymers thus obtained was adjusted to a solid content of 30%).

[Table 1]

Synthetic Examples of compounds A-1 to A-7*1								
Compound A		A-1	A-2	A-3	A-4	A-5	A-6	A-7
(a)	DETA*2	1.00	1.00	1.00	-	-	1.00	1.00
	TETA*3	-	-	-	1.00	1.00	-	-
(b)	Adipic acid	0.86	0.91	0.83	0.88	0.91	0.80	0.88
	Acid value of intermediate condensate*4	18	19	15	20	20	21	18
(c)	Acrylic acid	-	0.09	-	0.14	0.10	-	0.10
	Methacrylic acid	0.14	-	0.17	-	-	0.16	-
	Acid value of final condensate*5	19	19	17	19	21	20	17
(d)	Ethylene oxide	2.0	2.0	5.0	3.0	2.0	1.0	3.0
	Propylene oxide	-	2.0	-	1.0	-	2.0	-

*1 Components (a)-(d) used to produce compound A in the Table correspond to the compounds a to d described above, and each numeral value shows structural molar ratio.

*2 Diethylene triamine

*3 Triethylene tetramine

*4 Acid value of condensate (intermediate condensate) of compound a and compound b

*5 Acid value of condensate (final condensate) of compound a, compound b and compound c

[Table 2]

Example 1-9*1									
Example No.	1	2	3	4	5	6	7	8	9
Compound A									
A-1	20	-	-	-	-	-	-	-	-
A-2	-	20	-	-	-	-	-	-	-
A-3	-	-	15	-	-	-	-	-	-
A-4	-	-	-	30	-	-	-	25	-
A-5	-	-	-	-	25	-	-	-	13
A-6	-	-	-	-	-	33	-	-	-
A-7	-	-	-	-	-	-	20	-	-

*1 Value of compounds A-C in the Table is structural weight part on the basis of solid content

EP 1 184 353 A1

[Table 2] (continued)

Example 1-9*1									
Example No.	1	2	3	4	5	6	7	8	9
Compound B									
Na acrylate	-	20	27	-	-	12	-	-	-
NH ₄ acrylate	-	-	-	-	-	-	15	-	-
Na methacrylate	20	-	-	15	20	-	-	20	14
Compound C									
C-1*2	-	60	-	-	-	-	-	-	-
C-2*3	-	-	-	55	-	-	-	-	-
C-3*4	-	-	58	-	-	-	-	55	-
C-4*5	60	-	-	-	55	-	-	-	-
C-5*6	-	-	-	-	-	55	-	-	73
C-6*7	-	-	-	-	-	-	65	-	-
Weight average molecular weight of copolymer (x 10 ³)	32.0	35.1	42.5	35.3	37.5	30.7	47.2	44.2	38.5

*1 Value of compounds A-C in the Table is structural weight part on the basis of solid content

*2 Methoxypolyethylene glycol acrylate (molecular weight 400)

*3 Methoxypolyethylene glycol methacrylate (molecular weight 1,000)

*4 Methoxypolyethylene glycol acrylate (molecular weight 2,000)

*5 Methoxypolyethylene glycol methacrylate (molecular weight 2,000)

*6 Propoxypolyethylene glycol acrylate (molecular weight 3,000)

*7 Methoxypolyethylene glycol methacrylate (molecular weight 3,000)

Comparative Examples 1-4

[0044] Condensation compounds were synthesized in the same manner as in Example 1 except that reaction proportion of polyalkylene polyamine and dibasic acid and (meth)acrylic acid was out of the range described in the present invention (compounds A'-1 to compounds A'-4). Table 3 shows the Synthetic Examples.

[0045] These compounds A'-1 to compounds A'-4, compound B and compound C were copolymerized to obtain water soluble amphoteric copolymers (Comparative Examples 1-6). Table 4 shows the Synthetic Examples.

[Table 3]

Synthetic Examples of compounds A'-1 to compounds A'-4*1					
Comparative compound A'		A'-1	A'-2	A'-3	A'-4
(a)	DETA*2	1.00	1.00	-	1.00
	TETA*3	-	-	1.00	-
(b)	Adipic acid	0.60	0.80	0.70	0.97
	Acid value of intermediate condensate*4	18	19	20	23
(c)	Methacrylic acid	0.75	0.50	0.50	0.04
	Acid value of final condensate*5	17	18	18	25
(d)	Ethylene oxide	2.0	5.0	3.0	2.0

*1 Components (a)-(d) used to produce compound A' in the Table correspond to the compounds a to d described above, and each numeral value shows structural molar ratio.

*2 Diethylene triamine

*3 Triethylene tetramine

*4 Acid value of condensate (intermediate condensate) of compound a and compound b

*5 Acid value of condensate (final condensate) of compound a, compound b and compound c

[Table 4]

Comparative Examples 1-6*1						
Comparative Example No.	1	2	3	4	5	6
Compound A'						
A'-1	20	-	-	-	-	-
A'-2	-	15	-	-	-	-
A'-3	-	-	15	-	-	-
A'-4	-	-	-	20	-	-
Compound B						
Na methacrylate	20	25	25	25	40	35
Compound C						
C-1*2	60	-	-	-	-	-
C-2*3	-	-	60	-	60	-
C-3*4	-	60	-	-	-	-
C-4*5	-	-	-	55	-	65
Weight average molecular weight of copolymer ($\times 10^3$)	47.3	49.7	39.5	40.5	42.5	38.7

*1 Value of compound A', compound B and compound C in the Table is structural weight part on the basis of solid content

*2 Methoxypolyethylene glycol acrylate (molecular weight 400)

*3 Methoxypolyethylene glycol methacrylate (molecular weight 1,000)

*4 Methoxypolyethylene glycol acrylate (molecular weight 2,000)

*5 Methoxypolyethylene glycol methacrylate (molecular weight 2,000)

II. Test Example 1: Evaluation of water soluble amphoteric copolymer in ultrahigh performance concrete

[0046] In this Test Example, test was conducted for the purpose of a concrete that "shows slump flow of 60 cm or more in 2 hours after production of a ready-mixed concrete without material separation, starts to set within 24 hours, and has a compression strength of 150 N/mm² or more on the 91st day" as an ultrahigh performance concrete. Silica fume was used as a powder together with a cement (those in combination is called a binder), and the test of water soluble amphoteric copolymer was conducted using the concrete formulation shown in Table 5 under the condition that a water/binder ratio is 16% and 12%.

[0047] Mixing of a concrete was done by a 50 liters forced twin-screw mixer, and after cement, silica fume, fine aggregates, coarse aggregates and water having 1/2 amount of water soluble amphoteric copolymer cement dispersant dissolved therein were added and mill-mixed for 60 seconds, the remaining water soluble amphoteric copolymer was added to the mixer, followed by mill-mixing for 150 seconds.

[0048] Slump, slump flow and external quality were determined immediately after discharge, after 1 hour and after 2 hours and the concrete left to standing in a thermostatic chamber at 20°C was examined if setting begun within a predetermined period of time as well as a compression strength after 91 days.

[0049] Slump was measured according to JIS A-1101, slump flow was measured according to JASS5-T503, and compression strength was measured according to JIS A-1108.

[0050] The amount of the water soluble amphoteric copolymer added to the binder was determined in such a way that slump flow immediately after discharge was about 65 cm and tests were conducted with the amount of copolymer corresponding to slump flow of 65cm or less when no further effect was achieved even by the extra addition as in Comparative Examples 5 and 6 shown in Table 6 and Comparative Examples 3 and 4 shown in Table 7.

[0051] As is obvious from the results shown in Table 6, concretes with good condition were obtained by the water soluble amphoteric copolymers of Examples 1-9 even under the condition that the amount of water was extremely small signified by the water/binder ratio of 16%, and further the slump flow of 60 cm or more that satisfies the criterion of workability lasted for over 2 hours.

[0052] Further, since setting begins within 24 hours, there was no problem on hardening.

[0053] Table 7 shows test results of 12% water/binder ratio which is far beyond the common knowledge of concrete engineering, but a concrete with good condition was obtained by the water soluble amphoteric copolymer of the present invention, and slump flow of 60 cm or more over 2 hours that is a standard of workability was achieved. Further, there was no problem on hardening since setting begins within 24 hours and it is obvious that contribution to concrete en-

EP 1 184 353 A1

gineering by a water soluble amphoteric copolymer by the present invention was really immense.

[Table 5]

Formulation of concrete (unit: kg/m ³)		
Formulation No.	Formulation-1	Formulation-2
W/B (%)	16.0	12.0
Water*1	140	150
Cement*2	788	1125
Silica fume*3	88	125
Fine aggregates*4	529	381
Course aggregates*5	970	765

*1 City water

*2 In Formulation-1, moderate heat Portland cement (specific gravity 3.21) In Formulation-2, low heat Portland cement (specific gravity 3.22)

*3 Microsilica (product of L Chem. Co.)(specific gravity 2.20)

*4 Land sand from Kimitsu (specific gravity 2.63)

*5 Crushed stone from Kudamatsu City (specific gravity 2.74)

[Table 6]

Concrete test result [Case of using concrete fomulation-1 (W/B=16%)]

Test No.	Copolymer No.	Amount added ^{*1}	Slump (cm) ^{*2}		Slump Flow (cm) ^{*2}	
			Immediately after	1 Hour 2 Hours after	Immediately after	1 Hour 2 Hours after
1	Example 1	0.90	≥25	≥25	66.0	64.5 62.5
2	Example 2	1.00	≥25	≥25	65.0	63.0 61.5
3	Example 3	1.10	≥25	≥25	64.0	62.0 60.5
4	Example 4	1.10	≥25	≥25	65.5	64.5 63.5
5	Example 5	0.90	≥25	≥25	65.5	63.5 61.5
6	Example 6	0.90	≥25	≥25	66.0	64.0 61.5
7	Example 7	0.90	≥25	≥25	65.5	63.5 62.5
8	Example 8	1.10	≥25	≥25	65.0	64.5 63.0
9	Example 9	0.90	≥25	≥25	66.5	63.5 60.0
10	Comparative Example 1	1.50	≥25	21	65.5	53.0 36.0
11	Comparative Example 2	2.00	≥25	n.d.	63.5	n.d. n.d.
12	Comparative Example 3	1.80	≥25	19 12	62.0	34.5 24.5
13	Comparative Example 4	2.00	≥25	n.d.	63.5	n.d. n.d.

[Table 6 cont'd]

Test No.	Copolymer No.	Amount added* ¹	Slump(cm)* ²		Slump flow(cm)* ²	
			Immediately after	1 Hour 2 Hours after	Immediately after	1 Hour 2 Hours after
14	Comparative Example 5	2.50	15	n.d. n.d.	35.0	n.d. n.d.
15	Comparative Example 6	2.80	17	n.d. n.d.	36.0	n.d. n.d.

*1 Showing amount added (solid content) of cement dispersant to binder. Unit is wt%.

*2 Numeral values are all those of slump or slump flow (unit: cm), the expression "n.d." means that measurement cannot be made, because of excessive separation of fine aggregates & coarse aggregates.

[Table 6 cont'd]

Test No.	Copolymer No.	Appearance*3	Setting*4	Compression strength (N/mm ²)
1	Example 1	O	present	184
2	Example 2	O	present	180
3	Example 3	O	present	182
4	Example 4	O	present	178
5	Example 5	O	present	185
6	Example 6	O	present	185
7	Example 7	O	present	173
8	Example 8	O	present	180
9	Example 9	O	present	178
10	Comparative Example 1	O	present	170
11	Comparative Example 2	XX	present	-
12	Comparative Example 3	X	none	160
13	Comparative Example 4	XX	none	-
14	Comparative Example 5	XX	none	-
15	Comparative Example 6	XX	none	-

*3 "O" indicates the good condition of concrete, "X" indicates separation tendency of fine aggregates & coarse aggregates, and "XX" indicates apparent material separation.

*4 "present" when setting started within 24 hours, and "none" when setting did not start within 24 hours.

[Table 7]

Concrete test result [Concrete Formulation-2 (W/B=12%)]

Test No.	Copolymer No.	Amount added*1	Slump (cm) *2		Slump flow (cm) *2	
			Immediately	After	Immediately	1 Hour 2 Hours after
21	Example 1	2.50	≥25	≥25	≥25	64.5 62.5 60.0
22	Example 2	2.70	≥25	≥25	≥25	66.0 63.0 60.5
23	Example 4	2.50	≥25	≥25	≥25	64.0 62.0 60.5
24	Example 5	2.75	≥25	≥25	≥25	65.0 62.0 60.0
25	Comparative					
	Example 1	3.50	≥25	≥25	≥25	64.5 59.0 42.0
26	Comparative					
	Example 3	4.00	18	11	4	28.5 22.5 -
27	Comparative					
	Example 4	4.50	16	8	2	26.0 - -

*1: Amount added (solid content) of cement dispersant to binder. Unit is wt%.

*2: "-" means that measurement has no significance and was therefore terminated.

[Table 7 cont'd]

Test No.	Copolymer No.	Appearance*3	Setting*4	Compression strength (N/mm ²)
21	Example 1	0	present	172
22	Example 2	0	present	175
23	Example 4	0	present	166
24	Example 5	0	present	165
25	Comparative			
	Example 1	X	none	165
26	Comparative			
	Example 3	X	none	145
27	Comparative			
	Example 4	X	none	130

*3 "0" indicates the good condition of concrete, "X" indicates separation tendency of fine aggregates & coarse aggregates, and "XX" indicates apparent material separation.

*4 "present" when setting started within 24 hours, and "none" when setting did not start within 24 hours.

EP 1 184 353 A1

III. Test Example 2: Evaluation of water soluble amphoteric copolymer as high performance AE water reducing agent

[0054] The water soluble amphoteric copolymer of the present invention was tested within as well as outside of the use-limit of water for not only an ultrahigh performance concrete but also a concrete as high performance AE water reducing agent defined in JIS-A6204.

[0055] Here, the water soluble amphoteric copolymer of the present invention and the copolymer described in Example 1 of JP-A 7-33496 as Comparative Example 7 in this test were tested using the concrete formulation shown in Table 8 under the condition that a water/cement ratio is 28%. When kneading concrete, all materials of cement, fine aggregates, coarse aggregates and water having the copolymer to be tested dissolved therein were added and mixed with a 50 liters forced twin-screw kneading mixer for 90 seconds.

[0056] Slump, slump flow and external quality of the concrete were determined immediately after discharge, after 30 minutes and after 1 hour, and the concrete left standing in a thermostatic chamber at 20°C was examined if setting initiates within 10 hours.

[0057] As is evident from the results shown in Table 9, the water soluble amphoteric copolymer obtained by the present invention can suitably be used for not only an ultrahigh performance concrete, but a ready-mixed concrete at or over the upper limit of use for high performance AE water reducing agent defined in JIS-A6204. Contrary to this, slump and slump flow after 1 hours were extremely lower, poor external quality with a problem on hardening were observed in Comparative Example 7 in which compound A differs from the copolymer of the present invention. The effect according to the present invention observed herewith is far superior to the effect possibly predicted from the prior art in the pertinent art.

[Table 8]

Formulation of concrete (unit: kg/m ³)	
Formulation No.	Formulation-3
W/C (%)	28.0
Water*1	165
Cement*2	590
Fine aggregates*3	647
Course aggregates*4	964

*1 City water

*2 The blend of three brands with equivalent amount of General Portland cement (specific gravity 3.16)

*3 Land sand from Kimitsu (specific gravity 2.63)

*4 Lime crushed stone from Torikabayama (specific gravity 2.70)

[Table 9]
Concrete test result [Concrete Formulation-3]

Test No.	Copolymer No.	Addition amount*1	Slump (cm)		Slump flow (cm)	
			Immediately	Half hour 1 Hour	Immediately	Half hour 1 Hour
			after		after	
31	Example 1	0.40	≥25	≥25	63.0	64.0
32	Example 5	0.40	≥25	≥25	65.0	63.0
33	Comparative					
	Example 7	0.60	≥25	19	66.0	54.0
						35.0

*1: Amount added (solid content) of cement dispersant to binder. Unit is wt%.

[Table 9 cont'd]

Test No.	Copolymer No.	Appearance* ²	Setting* ³
31	Example 1	O	present
32	Example 5	O	present
33	Comparative		
	Example 7	X	none

*2 "O" indicates satisfactory condition of concrete by visual observation, and "X" indicates ununiform mixing of fine aggregates & coarse aggregates.

*3 "present" when setting started within 10 hours, and "none" when setting did not start within 10 hours.

Industrial Applicability

[0058] As described above in detail, the cement dispersant of the present invention has a very high water reducing effect and a very excellent slump flow retention, and is suitable for not only a cement dispersant for a usual concrete, but also a dispersant for an ultrahigh performance concrete represented by, in particular, a high-flow concrete. Moreover, the above mentioned water soluble amphoteric copolymer according to the present invention can be used appropriately as a high performance AE water reducing agent among other uses.

[0059] The concrete composition of the present invention to which the cement dispersant of the present invention having the above-mentioned excellent properties is blended is very good in water reducing effect, slump flow retention and strength development and the like, and is thus excellent in field workability.

[0060] Thus, the present invention provides a dispersant and a water reducing agent desired in the present field, and contribution to the pertinent field is tremendous.

Claims

1. A cement dispersant comprising as the main component of a water-soluble amphoteric copolymer obtained by copolymerizing an addition compound (compound A) obtained by addition of 0-8 moles of an alkylene oxide having 2 to 4 carbon atoms to one equivalent of amino residue in polyamide polyamine obtained by condensation of 1.0 mole of a polyalkylene polyamine, 0.8-0.95 mole of a dibasic acid or an ester of the dibasic acid with a lower alcohol having 1 to 4 carbon atoms, and 0.05-0.18 mole of acrylic acid or methacrylic acid, or an ester of acrylic acid or methacrylic acid with a lower alcohol having 1 to 4 carbon atoms, and a compound (compound B) of the formula I:



(wherein, R is hydrogen atom or methyl group, and M is hydrogen atom, an alkali metal, ammonium group or alkanolammonium group); and a compound (compound C) of the formula II:



(wherein, R' is hydrogen atom or methyl group, R₁ is C₂-C₄ alkylene group, R₂ is hydrogen atom or C₁-C₄ alkyl group, and m is an Integer of 1 to 100), in the ratio of compound A : compound B : compound C = 10-40% by weight : 10-40% by weight : 50-80% by weight.

2. The cement dispersant as claimed in claim 1, which is compounded with an ultrahigh performance concrete composition.
3. A concrete composition containing the cement dispersant as claimed in claim 1.
4. The concrete composition as claimed in claim 3, which is for an ultrahigh performance concrete.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP99/07261

A. CLASSIFICATION OF SUBJECT MATTER

Int.Cl⁷ C04B24/26, C04B103:40, C08F290/06, C08F299/02, B01F17/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

Int.Cl⁷ C04B24/26, C04B103:40, C08F290/06, C08F299/02, B01F17/00

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Jitsuyo Shinan Koho	1926-1996	Toroku Jitsuyo Shinan Koho	1994-2000
Kokai Jitsuyo Shinan Koho	1971-2000	Jitsuyo Shinan Toroku Koho	1996-2000

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

DIALOG (WPI/L)

Cement dispersing agent*acrylic acid*dibasic acid*polyalkylene-polyamine

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	JP, 7-33496, A (Toho Chem. Ind. Co., Ltd.), 03 February, 1995 (03.02.95) (Family: none)	1-4

☐ Further documents are listed in the continuation of Box C.☐ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not

considered to be of particular relevance

"E" earlier document but published on or after the international filing

date

"L" document which may throw doubts on priority claim(s) or which is

cited to establish the publication date of another citation or other

special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other

means

"P" document published prior to the international filing date but later

than the priority date claimed

"T" later document published after the international filing date or

priority date and not in conflict with the application but cited to

understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be

considered novel or cannot be considered to involve an inventive

step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be

considered to involve an inventive step when the document is

combined with one or more other such documents, such

combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

14 March, 2000 (14.03.00)

Date of mailing of the international search report

21 March, 2000 (21.03.00)

Name and mailing address of the ISA/

Japanese Patent Office

Authorized officer

Facsimile No.

Telephone No.